

AQUARIS white WB basecoat for lacquered, high solid content – for exteriors

Renner Italia Spa - Via Ronchi Inferiore, 34 - 40061 MINERBIO (BO)

Main properties:

Excellent sanding properties	High thixo properties
Excellent build	High solid content

Versions

versions:				
YLC108/C02 white	YLC108/NTR	Neutral	1	

Recommended use:	Frames windowShuttersEntrance doors	Garden furniture Gazeboes	Roof benches Matchboards for exteriors		
Application method:	automatic and manual spray, both airless and airmix, with or without electrostatic. n method: For horizontal and vertical application NTR version can be pigmented by adding EYM460 or EYM690 paste at a 2-3% ratio.				
Product preparation:	Ready to use.				

Chemical-Physical Properties at 23°C

Solid content (%)	C02:	58 ± 1			
Solid Content (%)	NTR:	54 ± 1			
Chapitia weight (g/am3)	C02:	$1,30 \pm 0,03$			
Specific weight (g/cm³)	NTR:	1,23 ± 0,03			
Viscosity Brookfield (mPas)					
suction no. 5 speed 20	6000 ± 500				

/ ippii dation distributed					
Max verticality (µm wet)	250 μm				
N. of coats	1				

Application characteristics

Recommended quantity min: 200 µm max: 250 µm

General remarks on the coating system

Drying at 23°C e RH% between 45 and 65: 150 µm					
Vertical stack ability	16 h				
Sandable	24 h				

Forced drying: 150 µm					
101000	ymg. Too piin				
Flash Off	room	15 minutes			
Laminar air	30°C	60 minutes			
Cooling	room	15 minutes			
Vertical stack ability	Downloaded from tunnel				
Sandable	24 h				

Support prepara		l be previoulsy treat	ed with	a pigmented wb impre	gnant	for exterior of AQUAR	IS range.	
Application instruction:		Dilution %		Noozle		Air pressure (bar)	Air pressure (bar)
Conventional air	gun	6 - 10		2 - 2,5		+/- 4		
Airmix		2 - 6		11- 13		0,5 - 1	80 - 120	
Airless		2 - 6		11- 13		==	80 - 120	
The use of pre heaters (with temperatures between 30 and 40 °C) ensure better application constancy whatever it is the ambient room.								
sanding:	Manual	: ● (240-280)	Orbital	: ● (240-280)	Auto	omatic: • (240-280)	brushing: -	
Overcoating:								
Apply one coat o	f wb pigm	ented topcoat for e	xteriors,	series AQUARIS.				

For further information regarding our water-based products from our range please ask for or refer to our guide

General remarks

- Mix well the product before using it.
- If the product is stored in premises with a temperature between <u>5 and 35°C</u>, the shelf life is <u>18 months</u>.
- During the application, both for the substrate that for the environment, the temperature has to be <u>not below 15°C</u>. The films that are created below that temperature have chemical and mechanical resistance characteristics below the standard quality usually obtained.
- The coating residues (washing water, water of the cabins, exhausted paints) have to be disposed of according to current regulations. Do not dispose of into drains.
- The equipment has to be washed with water straight after use. If dry films have to be removed, use **AY M460**, leaving it to act for a night, then rinse with water.

What to do to	Add	% of use		
What to do to	Auu	%	Grams per 25 liters	
Slow down the basecoat drying	AYM450	1 - 2	250 - 500	
Prolong shelf life of used product	AYM435	0,100	25	
Improve thixo or viscosity	AYM455	0,100 - 0,400	25 - 100	
In case of cissing caused by environmental pollution	AYM457	0,200 – 1	50 - 250	

Page 1 of 1 Printed on 19/07/2021